



UNIVERSITI PUTRA MALAYSIA

**FORMALDEHYDE EMISSION AND PROPERTIES
OF PHENOL-FORMALDEHYDE-RESINATED OIL PALM WOOD**

MOHAMAD AMARULLAH

FH 2010 7



FORMALDEHYDE EMISSION AND PROPERTIES
OF PHENOL-FORMALDEHYDE-RESINATED OIL PALM
WOOD

MOHAMAD AMARULLAH

MASTER OF SCIENCE
UNIVERSITI PUTRA MALAYSIA
2010



FORMALDEHYDE EMISSION AND PROPERTIES OF PHENOL
FORMALDEHYDE-TREATED OIL PALM WOOD

By MOHAMAD
AMARULLAH

Thesis Submitted to the School of Graduate Studies, Universiti Putra
Malaysia,



in Fulfilment of the Requirements for the Degree of Master of Science

October 2010



•

DEDICATION

To my beloved parents, Rd. Hanny Kusumawati Pdk.and Fawzul Kabir, and my sisters, Aulia Fabia and Aulia Nikmah, for their love, support, patience, understanding, and encouraged me throughout this journey.

FORMALDEHYDE EMISSION AND PROPERTIES OF PHENOL
FORMALDEHYDE-TREATED OIL PALM WOOD

By MOHAMAD

AMARULLAH

October 2010

Chairman : Associate Professor Edi Suhaimi Bakar, PhD

Faculty : Forestry

It is known that impregnation of oil palm wood (OPW) with low molecular weight phenol formaldehyde (Lmw-PF) resin significantly improved the strength, dimensional stability, durability, and machining characteristics of the material. This treatment has shown a great potential to expand the usage of OPW for high-grade furniture and housing materials. However, the treated OPW releases high amount of formaldehyde emission (FE), i.e. more than 30 mg/L which is considered as mammalian hazardous. If this material is to be used for indoor application, its FE should be reduced to threshold limit of 0.1 mg/L or less. The main objective of this study was to determine the level and reduce the FE from phenol formaldehyde-treated OPW which was manufactured at different processing variables. The physical properties such as density percent gain, weight percent gain, water absorption, thickness swelling, density profile, and mechanical properties such as modulus of elasticity (MOE), modulus of rupture (MOR), compression strength, shear strength, and hardness of the treated OPW were also assessed.

In this study two approaches were carried out to reduce the FE. Firstly, by

improving the curing state of the resin through a modification of compression step and adopting a post treatment drying after the manufacturing. Secondly, incorporating urea in the treating solution (as formaldehyde catcher). Samples were treated with 15% w/w Lmw-PF using vacuum pressure. After treatment, the samples were dried with industrial microwave until reach moisture content of 50%. The samples were then hot pressed at 150°C for 45 min to a compression ratio 50% (from 40 to 20 mm thick) using various compression steps (12.5%-25%-50%, 12.5%-37.5%-50%, and 25%-50%). The compression steps were varied in combination with various post treatment drying (0, 24, and 48 h) in an oven at $103 \pm 2^{\circ}\text{C}$. The compression step of 12.5%-25%-50% produced the sample with the lowest FE, and it was chosen as the optimum compression step which would be used in the second study. For the second approach, the treatment with the optimum compression step (12.5%-25%-50%) was combined with addition of various concentration of urea granule (5, 10, and 15% based on solid weight of phenol) in the treating solution as formaldehyde catcher.

The results showed that implementation of post treatment drying and modifying compression step significantly ($P < 0.05$) reduced FE level of the treated OPW from 30 to 9 mg/L. It is acknowledged that the post treatment drying gave more effect on reduction of FE than that of modifying compression step. The sample treated using combination of compression step of 12.5%-25%-50% and post treatment drying of 48 h emitted the lowest FE

of 9 mg/L. Meanwhile the addition of urea was not significantly ($P > 0.05$) reduces the FE level of the samples.

In term of physical properties, it was found that the three type treatments (altering compression step, post drying treatment, and addition of urea granule) imparted various positive and negative effects on the properties of the treated OPW. In general, there was no significant effect ($P > 0.05$) of the compression step and post drying treatments on the density gain, but the additions of urea granule on the PF resin liquid increased the sample density gain. The compression step gave more effect on the resin load than the post treatment drying, and the addition of urea granule on the PF liquid only increased the resin load. The microwave pre-heating prior to the hot-pressing densification resulted in the better (shallower) density profile of the treated OPW than that of many particleboards. The thickness swelling (TS) and water absorption (WA) values of the treated OPW were not affected by the three treatments.

In term of mechanical properties, the three treatments also imparted various positive and negative effects on the properties of the treated OPW. Both the compression step and post treatment drying gave significant effects ($P < 0.05$) on bending strength (MOE and MOR) values of the treated OPW samples, in which the former gave more significant effects than the later. Combination of the compression step of 12.5%---+25%---+50% and post treatment drying of 48 h gave the highest MOE value (14,980 MPa), and compression step of 12.5%---+25%---+50% and post treatment drying of 0 h gave the highest MOR

value (121.08 MPa). The post treatment drying gave irregular effect of the MOE but it has negative effect on MOR due to cellulose degradation caused by long heating treatment. Whilst, addition of urea granule on the resin liquid gave no significant ($P > 0.05$) effect on both the MOE and MOR values of treated OPW. The compression strengths were mainly affected by post treatment drying, and there was a tendency that the longer post treatment drying gave the higher compressive strength. The post treatment drying gave a positive effect, but urea granule addition gave negative effect on the shear strength of the treated OPW. All the three treatments gave no significant effect ($P > 0.05$) on the hardness of the treated OPW. Compare to the untreated OPW, the impregnation treatment of the OPW with Lmw-PF resin increased the MOE for 5.5 times (from 2,157 MPa to 11,954 MPa), MOR for 6.1 times (from 15.9 MPa to 97.4 MPa), compression strength parallel to the grain for 5.6 times (from 15.7 MPa to 88.1 MPa), and shear strength for 5 times (from 2.0 MPa to 10 MPa).

Finally, It can be concluded that implementation of post treatment drying and modifying compression step significantly reduced the FE level and increased the physical and mechanical properties of OPW. The modified impregnation treatment can be applied to effectively modify low quality OPW into highgrade OPW that can be used as value added furniture and other high grade interior/exterior applications.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia
sebagai memenuhi keperluan untuk ijazah Master Sains

**EMISI FORMALDEHIDA DAN SIFAT-SIFAT KAYU SAWIT
YANG DIRAWAT DENGAN PHENOL FORMALDEHIDA**

Oleh

MOHAMAD AMARULLAH

Oktober 2010

Pengerusi : Professor Madya Edi Suhaimi Bakar, PhD

Fakulti : Perhutanan

Telah diketahui bahawa impregnasi kayu kelapa sawit (KKS) dengan fenol formaldehid resin berat molekul rendah (Lmw-PF) secara signifikan mempertingkatkan kekuatan, kestabilan dimensi, ketahanan, dan ciri pemrosesan bahan tersebut. Rawatan ini telah menunjukkan potensi yang besar untuk memperluaskan penggunaan KKS untuk perabot bermutu tinggi dan bahan perumahan. Walau bagaimanapun KKS yang dirawat membebaskan formaldehid pada kadar tinggi, iaitu lebih dari 30 mg/L yang dianggap sebagai tidak sihat kepada mamalia. Jika bahan ini akan digunakan untuk kegunaan dalaman, tahap pembebasan formaldehid (FE) mestilah dikurangkan kepada tahap selamat, iaitu 0.1 mg/L atau kurang. Tujuan utama kajian ini adalah untuk menentukan tahap FE dan mengurangkan FE daripada KKS yang dirawat melalui pengubahsuaian pembolehubah proses pembuatan. Sifat fizikal seperti pertambahan peratus

ketumpatan, pertambahan peratus berat, penyerapan air, pengembangan ketebalan, profil ketumpatan, dan sifat mekanik seperti modulus kenyalan (MOE), modulus pecah (MOR), kekuatan mampatan, kekuatan ricih, dan kekerasan daripada KKS yang dirawat juga dinilai.

Dalam kajian ini dua pendekatan dilakukan untuk mengurangkan FE.

Pertama, dengan mempertingkatkan tahap pematangan resin melalui pengubahsuaian langkah mampatan dan menggunakan rawatan pasca pengeringan selepas proses pembuatan. Kedua, menambahkan urea ke dalam cecair perawat (sebagai penangkap formaldehid). Sampel dirawat dengan menggunakan 15% *b/b* Lmw-PF menggunakan proses vakum mampatan. Selepas rawatan, sampel dikeringkan dengan gelombang mikro industri sehingga kandungan lembapan mencapai 50%. Sampel kemudian dikenakan mampatan panas pada 150°C selama 45 min kepada nisbah mampatan 50% (dari ketebalan 40 mm kepada 20 mm) dengan langkah mampatan yang pelbagai (12.5%--+25%--+50%, 12.5%--+37,5%--+50%, dan 25%--+50%). Langkah mampatan yang berbeza-beza digabungkan dengan pelbagai perlakuan pasca pengeringan yang pelbagai (0,24, dan 48 jam) di dalam oven pada suhu 103±2 °C. Langkah mampatan 12.5%--+25%--+50% menghasilkan sampel dengan FE terendah, Langkah ini dipilih sebagai optimum yang digunakan dalam kajian kedua. Untuk pendekatan kedua, perlakuan dengan langkah mampatan optimum (12.5%--+25%--+50%) yang digabungkan dengan penambahan butir urea dengan pelbagai kepekatan (5, 10, dan 15% berdasarkan berat pepejal fenol) ke dalam cecair rawatan sebagai penangkap formaldehid.

Keputusan menunjukkan bahawa pelaksanaan rawatan pasca pengeringan dan mengubahsuai langkah mampatan signifikan ($P < 0.05$) dapat menurunkan kadar FE dari KKS dirawat dari 30 mg/L kepada 9 mg/L. Hal ini diakui bahawa rawatan pasca pengeringan memberikan kesan yang lebih kepada pengurangan FE dibandingkan dengan mengubahsuai langkah mampatan. Sampel yang dirawat dengan menggunakan gabungan antara langkah mampatan 12.5%-25%-50% dan rawatan pasca pengeringan 48 jam memberikan pembebasan FE terendah pada 9 mg/L. Sementara itu penambahan urea tidak secara signifikan ($P > 0.05$) mengurangkan kadar FE sampel.

Dalam hal sifat fizikal, didapati bahawa tiga jenis perlakuan (pengubahsuaian langkah mampatan, rawatan pasca pengeringan, dan penambahan butiran urea) memberikan pelbagai kesan positif dan negatif terhadap sifat KKS yang dirawat. Secara amnya, tiada kesan signifikan ($P > 0.05$) dari pembolehubah langkah mampatan dan rawatan pasca pengeringan pada pertambahan ketumpatan, tetapi penambahan butir urea pada cecair resin PF meningkatkan pertambahan ketumpatan sampel. Langkah mampatan memberikan pengaruh yang lebih pada pembebanan resin daripada rawatan pasca pengeringan, dan penambahan butir urea pada cecair PF hanya meningkatkan pembebanan resin. Pemanasan gelombang mikro sebelum pemadatan panas pada KKS yg dirawat menghasilkan profil ketumpatan yang lebih baik (lebih dangkal) berbanding profil ketumpatan daripada kebanyakan papan serpai. Nilai pengembangan ketebalan (TS) dan

penyerapan air (WA) dari KKS yang dirawat tidak dipengaruhi oleh ketiga rawatan tersebut.

Dalam hal sifat mekanik, tiga rawatan ini juga memberikan pelbagai kesan positif dan negatif terhadap KKS yang dirawat. Kedua-dua langkah mampatan dan rawatan pasca pengeringan memberikan pengaruh yang signifikan ($P < 0.05$) terhadap nilai kekuatan lenturan (MOE dan MOR) sampel KKS dirawat, dimana langkah mampatan lebih memberi pengaruh daripada rawatan pasca pengeringan. Kombinasi langkah mampatan 12.5%-25%-50% dan rawatan pasca pengeringan 48 jam memberikan nilai MOE tertinggi (14,980 MPa), manakala langkah mampatan 12.5%-25%-50% dan rawatan pasca pengeringan 0 h memberikan nilai MOR tertinggi (121.08 MPa). Perlakuan pasca pengeringan memberikan kesan yang tidak sarna terhadap MOE, tetapi memberikan kesan negatif terhadap MOR kerana disebabkan penguraian selulosa akibat pemanasan yang lama. Sementara itu, penambahan butir urea granula di dalam cecair resin tidak memberikan kesan signifikan ($P > 0.05$) terhadap nilai MOE dan MOR dari KKS yang dirawat. Kekuatan mampatan terutama dipengaruhi oleh rawatan pasca pengeringan, dan ada kecenderungan bahawa perlakuan pasca pengeringan lagi memberikan nilai kekuatan mampatan yang lebih tinggi. Perlakuan pasca pengeringan memberikan pengaruh positif, sedangkan penambahan butir urea memberikan kesan negatif pada kekuatan ricih dari KKS yang dirawat. Semua tiga perlakuan tidak memberikan pengaruh yang signifikan ($P > 0.05$) terhadap kekerasan KKS yang dirawat. Apabila dibandingkan dengan KKS tidak dirawat, rawatan

pemadatan dari KKS dengan resin Lmw-PF mampu meningkatkan MOE sebanyak 5.5 kali ganda (dari 2,157 MPa kepada 11,954 MPa), nilai MOR sebanyak 6.1 kali ganda (dari 15.9 MPa kepada 97.4 MPa), kekuatan mampatan selari ira sebanyak 5.6 kali ganda (dari 15.7 MPa kepada 88.1 MPa), dan kekuatan ricih sebanyak 5 kali ganda (dari 2.0 MPa kepada 10 MPa).

Akhirnya, dapat disimpulkan bahawa pelaksanaan rawatan pasca pengeringan dan mengubahsuai langkah mampatan secara signifikan boleh mengurangkan kadar FE dan meningkatkan sifat fizikal dan mekanikal KKS. Rawatan pemadatan diubahsuai dapat diterapkan secara berkesan mengubahsuai KKS bernutu rendah menjadi KKS bermutu tinggi sehingga boleh digunakan untuk pembuatan perabot yang bernilai tinggi samada untuk kegunaan dalarnan ataupun luaran.

ACKNOWLEDGEMENTS

First and foremost my gratitude is to Allah S.W.T. for giving me strength to compete this thesis. I wish to express my deepest gratitude to Associate Professor Dr. Edi Suhaimi Bakar, my main supervisor, for his patience, support, guidance, and advice toward completion my thesis, and sponsoring this whole project. My appreciations go to my co-supervisors; Associate Professor Dr. Zaidon Ashaari for his encouragement and support to this research. I am sincerely thankful and greatly appreciative for FRIM sawmilling staff for helping the samples preparations, Dong Hwa Sdn. Bhd. for profile density measurement and everyone who assisted me in this project. Thanks to all staffs of Faculty of Forestry especially Wood Composite Lab staffs; Izuddin, Mr. Zamani and Topo for their help upon completing the project. I would also like to thanks to Mr. Rizal from Material Testing Lab. for his help and guidance upon mechanical testing projects. Thanks to Wood Chemistry Lab Members; Juliana, Kak Nora, Kak Hafiz, Sim Hong, Thye Siang, Janet, Khaf, Juhaida and Aisyah for their non-exhaustive energy. A special thanks to my lab mates; Pian, Chong, and Farin, thank you so much for our unforgettable moments. Not forgetting to all Indonesian student association on UPM, my housemate (719) for our friendship in these couple of years. Last but not least, I want to thank to my family and Anissa Soraya for their love, support, and encouragement throughout my study.

I certify that a Thesis Examination Committee has met on 29 October 2010 to conduct the final examination of Mohamad Amarullah on his thesis entitled "Formaldehyde Emission and Properties of Phenol Formaldehyde-Treated Oil Palm Wood" in accordance with the Universities and University College Act 1971 and the Constitution of the Universiti Putra Malaysia [P.U.(A) 106] 15 March 1998. The committee recommends that the student be awarded the Master of Science.

Members of the Thesis Examination Committee were as follows:

Mohd Hamami bin Sahri, PhD Professor

Faculty of Forestry Universiti Putra

Malaysia (Chairman)

Mohd Zin b Jusoh, PhD Associate

Professor Faculty of Forestry

Universiti Putra Malaysia (Internal
Examiner)

H'Ng Paik San, PhD Lecturer

Faculty of Forestry Universiti Putra

Malaysia (Internal Examiner)

Abdul Khalil bin Shawkataly, PhD Professor

School of Industrial Technology Universiti

Sains Malaysia (External Examiner)

~

Professor an~Deputy Dean School of Graduate Studies Universiti Put a Malaysia

Date: 22 February 2011



This thesis was submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfilment of the requirement for the degree of Master of Science. The members of the Supervisory Committee were as follows:

Edi Suhaimi Bakar, PhD

Associate Professor Faculty of
Forestry Universiti Putra Malaysia
(Chairman)

Zaidon Ashaari, PhD

Associate Professor Faculty of
Forestry Universiti Putra Malaysia
(Member)




HASANAH MO'D. GHAZALI, PhD
Professor and Dean
School of Graduate Studies Universiti
Putra Malaysia

Date: 10 MAR 2011

DECLARATION

I declare that the thesis is my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously, and is not concurrently, submitted for any other degree at Universiti Putra Malaysia or at any other institution.



MOHAMAD AMARULLAH

Date: 29 October 2010

TABLE OF CONTENTS

	Page
DEDICATION	iii
ABSTRACT	IV
ABSTRAK	viii
ACKNOWLEDGEMENT	xiii
APPROVAL	XIV
DECLARATION	xvi
LIST OF TABLES	xx
LIST OF FIGURES	xxi
LIST OF ABBREVIATION	XXIII
 CHAPTER	
 1 INTRODUCTION	 1
1.1 Background	1
1.2 Problem Statement	4
1.3 Objectives	7
 2 LITERATURE REVIEW	 8
2.1 Forest Trend and Wood Demand	8
2.2 Policy of Industry	9
2.3 Development of Oil Palm Plantation	11
2.4 History and Botanical Description	13
2.5 Replanting of Matured Oil Palm and Its Biomass Utilization	14
2.6 Oil Palm Wood and Its Products	18
2.7 Oil Palm Wood Characteristics	20
2.7.1 Anatomy	21
2.7.2 Chemical Properties	24
2.7.3 Physical Properties	25
	xvii

2.7.4 Mechanical Properties	28
Machining Behavior	31
Durability	31
2.8 Phenol Formaldehyde Resin	32
2.8.1 Characteristics of Low Molecular Weight Phenol Formaldehyde	34
2.8.2 Physical and Chemical Characteristics of Phenol Formaldehyde	36
2.9 Formaldehyde Emission	37
3 MATERIAL AND METHODS	41
3.1 Material and Sample Preparation	41
3.2 Low Molecular Weight Phenol Formaldehyde Preparation	42
3.3 Modified Compreg Treatment of OPW with Lmw-PF Resin	44
3.4 Determination of Formaldehyde Emission	48
3.4.1 Reagents	48
3.4.2 Test Pieces	48
3.4.3 Sample Collection	50
3.4.4 Determination of Formaldehyde	50
3.4.5 Formaldehyde Standard Solution	51
3.4.6 Determination of the Calibration Curve	52
3.4.7 Calculation of the Concentration of Formaldehyde Emission	52
3.4.8 Evaluation of Lmw-PF Polymerization	53
3.5 Evaluation of Physical Properties	53
3.5.1 Moisture Content	53
3.5.2 Weight Percent Gain	54
3.5.3 Density	55
3.5.4 Density Gain	55
3.5.5 Profile Density	56
3.5.6 Water Absorption and Thickness Swelling	56
3.6 Evaluation of Mechanical Properties	57
3.6.1 Static Bending Test	58

3.6.2 Compression Strength Parallel to The Grain

59

xviii

3.6.3	Shear Strength Parallel to The Grain	60
3.6.4	Janka Hardness	61
3.7	Data Analysis	62
4	RESULTS AND DISCUSSION	63
4.1	Introduction	63
4.2	Formaldehyde Emission	64
4.3	Physical and Mechanical Properties	70
4.3.1	Density and Density Gain	70
4.3.2	Weight Percent Gain	72
4.3.3	Density Profile	75
4.3.4	Water Absorption and Thickness Swelling	77
4.3.5	Static Bending Strength	80
4.3.6	Compression Strength Parallel to The Grain	83
4.3.7	Shear Strength and Hardness	84
4.4	Effect of Urea Addition In Lmw-PF on Formaldehyde Emission	86
4.5	Effect of Urea Addition on Properties	87
4.5.1	Density and Density Gain	88
4.5.2	Weight Percent Gain	89
4.5.3	Water Absorption and Thickness Swelling	90
4.5.4	Static Bending Strength	92
4.5.5	Compression Strength Parallel to The Grain	93
4.5.6	Shear Strength and Hardness	94
5	CONCLUSIONS AND RECOMENDA TIONS	96
5.1	Conclusions	96
5.2	Recommendations	99
	REFERENCES	100
	APPENDICES	105
	BIODATA OF THE STUDENT	107